


Pigments for Textile Printing



JIANGSU MULTICOLOR FINE CHEMICAL CO., LTD.
WUXI XINGUANG CHEMICAL INDUSTRY CO., LTD.

Pigments for Textile Printing

Multifast Pigments are medium and high class pigments serve Printing Inks, Coatings, Plastics, Textile industries.

Quinolor Pigments are developed with Japanese technology and are optimized for special applications as Offset Printing Inks etc.

Disclaimer: This information is based on our present state of knowledge and is intended to provide general note on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for particular applications.

Commodity Name	C. I.	Resistance							Remarks
		Heat	Light	Acid	Alkali	Linseed Oil	Paraffin Wax	Water	
Multifast Lemon Yellow		140	5	5	4	4	5	5	
Multifast Light Fast Yellow 10G	PY3	160	7	5	5	5	4	4-5	
Multifast Light Fast Yellow 10GL	PY3	160	7	5	5	5	4	4-5	Economic type.
Multifast Yellow GO	PY12	180	4	5	4-5	5	4-5	5	High hiding power
Multifast Yellow GL	PY12	180	4	5	4-5	5	4-5	5	Economic type.
Multifast Yellow GCW	PY12	160	4	5	4-5	5	4-5	5	Greenish, High Strength
Multifast Yellow GR	PY13	200	5	5	5	5	5	5	
Multifast Yellow 2GS	PY14	200	6	5	4	5	5	5	
Multifast Yellow 3GW	PY14	200	6	5	4	5	5	5	Greenish
Multifast Yellow GG	PY17	180	6-7	5	5	4	4-5	4-5	
Multifast Yellow 2RN	PY55								
Multifast Yellow 5GX	PY74	150	6	5	5	4-5	4-5	5	Opaque, Greenish
Multifast Yellow 5GW	PY74	150	6	5	5	4-5	4-5	5	Greenish, high strength.
Multifast Yellow H10G	PY81	200	6-7	5	5	5	5	5	
Multifast Yellow HR-120	PY83	220	7-8	5	5	5	5	5	Reddish, good fluidity, similar to Clariant's HR02
Multifast Yellow LR	PY83	200	7-8	5	5	5	5	5	Reddish. Economic grade.
Multifast Orange RN	PO5	150	6-7	5	4	4		4-5	
Multifast Orange RG	PO13	180	5	5	3	3-4	5	4	Reddish shade.
Multifast Orange R	PO16	160	4-5	3	4	4		5	
Multifast Orange RL	PO34	170	4-5	5	5	4-5		4	
Multifast Red 2R	PR2	160	6-7	3-4	5	2-3	4	5	
Multifast Red F4R	PR8	140	5	5	1-2	1-2	5	4-5	
Multifast Brilliant Red N	PR22	130	5	5	2	1-2	5	5	
Multifast Brilliant Red NB	PR22	130	5	5	2	1-2	5	4	Bluish, High Strength
Multifast Brilliant Red NY	PR22	130	5	5	2	1-2	5	5	Yellowish
Multifast Rose Red 3B	PR23	140	5-6	4	4-5		5	5	
Multifast Rose Red 2B	PR23	140	5-6	4	4-5		5	5	Economic type
Multifast Rose Red RB	PR23	140	5-6	4	4-5		5	5	Reddish
Multifast Rubber Bordeaux BF	PR31	150	5-6	5	4-5	4-5	5	5	
Multifast Rubber Bordeaux BFW	PR31	150	5-6	5	4-5	4-5	5	5	Good dispersion, good stability
Multifast Pyrazolone Red	PR38	180	6						

Commodity Name	C. I.	Resistance							Remarks
		Heat	Light	Acid	Alkali	Linseed Oil	Paraffin Wax	Water	
Multifast Red Toner CW	PR53:1	130	4	4-5	2	4	5	4-5	
Multifast Red FGR	PR112	140	5-6	5	5	3-4	5	5	
Multifast Red FGR110	PR112	140	5-6	5	5	3-4	5	5	Yellowish
Multifast Pink E	PR122	250	7	5	5	5	5	5	
Multifast Pink FBB01	PR146	180	5	5	4-5	4-5	5	5	Yellowish
Multifast Pink FBB02	PR146	200	5	5	4-5	4-5	5	5	Bluish
Multifast Red 2G	PR148	160	6-7	5	5	3	4-5	5	
Multifast Red F2RK	PR170	160	8	5	5	4		5	
Multifast Red F3RK	PR170	180	7-8	5	5	4		5	Yellowish.
Multifast Red F5RK	PR170	160	5	5	5	4		5	Bluish.
Multifast Pink B	PR245	170	5	5	5	4-5	4-5	5	
Multifast Violet E	PV19	250	7	5	5	5	5	5	Yellowish
Multifast Violet RL	PV23	200	7-8	5	5	5	5	5	Reddish, suitable for water system
Multifast Green G	PG7	200	7-8	5	5	5		5	
Multifast Blue B	PB15:0	200	7-8	5	5	5		5	
Multifast Blue BGS	PB15:3	200	7-8	5	5	5		5	



Jiangsu Multicolor Fine Chemical Co., Ltd.
Wuxi Xinguang Chemical Industry Co., Ltd.
Tel: +86(510)85217450 (central)
Fax: +86(510)85215284, 85212856
www.xinguangchem.com

Ms. Yuan Yanle
extension 9911
yuan@xinguang-chem.com

Mr. Frank Pan
extension 9922
zypan@vip.163.com

Mr. Wang Nengwu
extension 9010
wangnw@xinguang-chem.com